

## **Amendments to the Specification**

Please replace paragraph [0038] of the application (published version US 2006/0029788 A1) with the following amended paragraph:

[0038] IFD<sub>25</sub> or “indentation force defection” was determined in accord with a procedure ~~similar to~~ described in ASTM D 3574. In this case, foam was compressed by 25% of its original height and the force was reported after one minute. The foam samples were cut to a size 15”x15”x4” prior to testing.